

**Příloha 2: Specifikace cementové malty**

Sada	Formy	Cement		Ozn. Pytle	Vel. zrna [mm]	Recykliát		Celkem [g]	Procentuální množství [%]	Druh	16 % PVA				Celkem vody [g]	w/c [-]	
		Hmotnostní množství [g]	Procentuální množství [%]			I. mletí	II. mletí				Hm [g]	Pm [%]	Hm [g]	Pm [%]			
AS	AS1	42,5 R							0			525,0	35	84,2	5,6	440,8	0,29
	AS2																
BS	BS1	42,5 R							150	10		375	25	60,0	4	465,0	0,31
	BS2																
CS	CS1	42,5 R							262,5	17,5		262,5	17,5	42,0	2,8	483,0	0,32
	CS2																
DS	DS1	42,5 R							393,75	26,25		131,25	8,75	21,0	1,4	504,0	0,34
	DS2																
ES	ES1	42,5 R	975	65	< 0.25 mm	Ø 400	Ø 150	525	35	Pitná	1500	0	0	0,0	0	525,0	0,35
	ES2																
AV	AV1	42,5 R							0			525,0	35	84,2	5,6	440,8	0,29
	AV2																
BV	BV1	42,5 R							150	10		375	25	60,0	4	465,0	0,31
	BV2																
CV	CV1	42,5 R							262,5	17,5		262,5	17,5	42,0	2,8	483,0	0,32
	CV2																
DV	DV1	42,5 R							393,75	26,25		131,25	8,75	21,0	1,4	504,0	0,34
	DV2																
EV	EV1	42,5 R							525	35		0	0	0,0	0	525,0	0,35
	EV2																