

TYPE

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

2M5 U0-U2 HP W A

NA-789 CODE

COMPOSITION						
	material	polyurethane (TPU) - HP [®] system				
ng	thickness	0.20 mm <i>0.008 in.</i>				
Conveying surface	surface pattern	smooth				
	colour	white				
	coefficient of friction	MF				
le Ss	material	polyester (PET) - HP [®] system				
Textile carcass	plies no.	2				
	weft type	rigid				
	material	fabric w/polyurethane (TPU) impregn $\mathrm{HP}^{\mathrm{@}}$ system				
Driving surface	thickness	mm <i> in.</i>				
	surface pattern	fabric				
	colour	light blue				

TECHNICAL SPECIFICATIONS					
Total thickness	1.30 mm	0.05	in.		
Weight	$1.40~\text{kg/m}^{\text{2}}$	0.29	lbs./sq.ft		
Elongation at 1%	6 N/mm	34.3	lbs./in.		
Max. admissible pu	12 N/mm	69.0	lbs./in.		
Temperature resistance (1)	min.	-30 °C	-22	°F	
resistance (1)	max.	110 °C	230	°F	
(1) Use of the belt with limit values may reduce its life					
Minimum radius / d	iameter ⁽²⁾				

Knife edge minimum radius	4 mm	0,16 in.
Bending roller min. diameter	8 mm	0.31 in.
Counter-bending roller min_diameter	16 mm	0.63 in

 $^{\left(2\right)}\,$ The above mentioned values depend on the type of CHIORINO joint recommended

Coefficient of friction on driving surface 0.20 [-]

■ Raw steel sheet Laminated plastic/wood 0.25 [-] ■ Steel roller 0.20 [-] Rubberized roller 0.30 [-]

Max. production width 2000 mm 79 in.

SUITABLE FOR

Food: slicing machines Food: seafood processing


Food: dairy Food: bakery

Food: biscuits and crackers: rotary cutter

Food: chocolate industry Paper industry: tissue

Packaging

Pharmaceutics industry





FEATURES	
Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	
Conveying on skid bed	yes
Conveying on rollers	
Conveying on skid bed on top and return	
Troughed conveying	
Swan neck conveying	
Inclined conveying	
Accumulators belts	no
Curved conveyor	
Chemical resistances (see file available on line)	

COMPLIANCES

REACH Regulation EC 1907/2006 and amendments Regulation EC 1935/2004 and amendments Regulation EC 2023/2006 and amendments Regulation EU 10/2011 and amendments FDA (Food and Drug Administration)

USDA (United States Department of Agriculture)

NOTES

Thanks to the outstanding resistance to abrasion, oils, fats, detergents and to the most aggressive cleaning procedures, the HP product system is specially recommended for applications that require compliance with HACCP (Hazard Analysis and Critical Control Point) and IFS (International Food Standard).

Issue: 24-07-2008 Last Update: 23-06-2016

DISCLAIMER


The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



JOINTING TECHNICAL DATA SHEET

CODE NA-789 TYPE **2M5 U0-U2 HP W A**

Recommended jointing procedure SINGLE Z



Other jointing methods can be used:

DIAGONAL SINGLE Z DOUBLE Z SKIVED JOINT '1'


Check our general catalogue to get further info on CHIORINO jointing methods.

Pressing

Heating press P\PL\PLS


Press settings				
Upper platen temperature	155 °C			
Lower platen temperature	155 °C			
Temperature gauge setting	155 °C			
Curing time in press	3 min.			
Pressure	2 bar			
Film	TC-300 - HP W PU film			
Cement				

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
 A periodical inspection of the thermostats is recommended, to make sure they function correctly.

Layout of components



Notes

Issued: 29-10-2013 Last Update: 30-01-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.